

CUBE 25 1/2 H


Carico Rottura Breaking Load Rm N/mm ²	Carico Snervamento Enervation Load Rp 0,2 N/mm ²	Durezza Hardness HV	Conducibilità Conductivity Elettrica % IACS
590 - 690	510 - 660	180 - 220	15 - 19
Dimensioni - Dimensions		Peso Kg/m - Weight Kgs/m	
0,10 x 170		0,140	
0,15 x 170		0,210	
0,20 x 220		0,363	
0,25 x 220		0,453	
0,30 x 220		0,544	

CUBE 25 1/2 HM


Carico Rottura Breaking Load Rm N/mm ²	Carico Snervamento Enervation Load Rp 0,2 N/mm ²	Durezza Hardness HV	Conducibilità Conductivity Elettrica % IACS	Trattamento termico
930 - 1080	750 - 980	290 - 350	19 - 28	Già trattato Already treated
Dimensioni - Dimensions		Peso Kg/m - Weight Kgs/m		
0,10 x 170		0,140		
0,15 x 170		0,210		
0,20 x 220		0,363		

CUBE 25 XHMS


Carico Rottura Breaking Load Rm N/mm ²	Carico Snervamento Enervation Load Rp 0,2 N/mm ²	Durezza Hardness HV	Conducibilità Conductivity Elettrica % IACS	Trattamento termico
1200 - 1320	1030 - 1230	365 - 420	19 - 28	Già trattato Already treated
Dimensioni - Dimensions		Peso Kg/m - Weight Kgs/m		
0,15 x 170		0,210		
0,20 x 220		0,363		

CUBE 25 A


Carico Rottura Breaking Load Rm N/mm ²	Carico Snervamento Enervation Load Rp 0,2 N/mm ²	Durezza Hardness HV	Conducibilità Conductivity Elettrica % IACS
410 - 540	190 - 380	90 - 150	15 - 19
Dimensioni - Dimensions		Peso Kg/m - Weight Kgs/m	
0,30 x 220		0,544	
0,40 x 220		0,726	
0,50 x 220		0,907	
0,60 x 220		1,089	